


## SIEVE ANALYSIS REPORT

Washed Sieve: ASTM C136 and C117

Project No.: <u>ENG.KGEO03845-17</u> Project: <u>Highway 8 - Site 11 Major Works,</u> <u>BC MoT Proj. No. 26324-0002</u> Client: <u>BC Ministry of Transportation</u> Attention: <u>See e-mail distribution</u> Email: <u>See e-mail distribution</u> Description: <u>200 mm (-) GRAVEL, some sand, trace silt</u> Source: <u>Site 17 crusher site</u> Supplier: <u>N/A</u> Sample Location: <u>Site 17 stockpile</u> Specification: <u>N/A</u>	Sample No.: <u>KS-11213</u> Date Received: <u>May 23, 2025</u> Sampled by: <u>AS</u> Date Tested: <u>May 26, 2025</u> Tested by: <u>MV</u> Office: <u>Kelowna</u> Moisture Content (as received): <u>3.1%</u> No. Crushed Faces: <u>One (1) or Two (2)</u> By particle mass: _____
---	---

Sieve Size	Percent Passing
200	100
100	86
50	67
37.5	58
25	50
19	45
12.5	38
9.5	34
4.75	26
2.36	20
1.18	16
0.600	13
0.300	10
0.150	8
0.075	5.9



Remarks: \_\_\_\_\_

Reviewed By:  C.Tech.

Trevor Janicki

Data presented hereon is for the sole use of the stipulated client. Tetra Tech is not responsible, nor can be held liable, for use made of this report by any other party, with or without the knowledge of Tetra Tech. The testing services reported herein have been performed to recognized industry standards, unless noted. No other warranty is made. These data do not include or represent any interpretation or opinion of specification compliance or material suitability. Should engineering interpretation be required, Tetra Tech will provide it upon written request.

